

**BINDER FOR THICK-FILM PASTE**

**Patent number:** JP10036479  
**Publication date:** 1998-02-10  
**Inventor:** SUEHIRO MASATOSHI; KAWAZU KOICHI  
**Applicant:** DAI ICHI KOGYO SEIYAKU CO LTD;; DOWA MINING CO LTD  
**Classification:**  
**- international:** C08G18/48; C08G63/66; C08L67/02; C08L75/08; H05K1/09  
**- european:**  
**Application number:** JP19960193407 19960723  
**Priority number(s):**

[Report a data error here](#)

**Abstract of JP10036479**

**PROBLEM TO BE SOLVED:** To obtain a binder for thick-film pastes which remains no carbon even when baked in the atmosphere, a low-temperature range or an inert gas atmosphere by using a specified high-molecular compound having a specified average molecular weight or higher.  
**SOLUTION:** A dihydroxy compound having an average molecular weight of 1,000 or above and obtained by the addition polymerization of an alkylene oxide is reacted with a dicarboxylic acid, its anhydride or its lower alkyl ester or reacted with an isocyanate-terminated compound to obtain an ester-bond- containing or a urethane-bond-containing polymer compound having an average molecular weight of 20,000 or above. It is desirable that the polymer compound has 50wt.% or above alkylene oxide. The polymer compound is used as a binder for thick-film pastes.

---

Data supplied from the **esp@cenet** database - Patent Abstracts of Japan